

PRODUCT CODE 2256
ROSALEE N.C.PRIMER SURFACER WHITE

Scope

The four letters stand for nitro-cellulose primer surfacer. The main function is to even up any surface, which is wavy and to build up the film for better protection. Besides, being based on N.C. It must dry quickly to ensure faster production. The dry film, when wet sanded, must offer a silky smooth surface.

Areas of Application

Mostly, N.C.P.S is used while repainting any vehicle. But can also be used for special type furniture, like the one meant for computers.

Surface Preparation

Since primer-surfacer is always applied over a primed surface, nothing much is required to prepare the surface. However, the surface must be free from traces of oil and grease and to remove them, simple solvent wiping is good enough.

Technical Data

• APPEARANCE	: Free flowing viscous liquid indicating White shade.
• REDUCE VISCOSITY	: 25 ± 3 seconds in ford cup no.4 @ 30o c. THINNER (1:1) NCGP
• SPRAYING VISCOSITY	: 20 to 25 sec.
• THINNER TO BE USED	: N.C. Thinner 033
• WEIGHT PER LITRE	: 1.20 ± 0.02 kg./ltr.
• DRYING TIME	: Touch dry : 5-10 minutes
• SURFACE DRY	: 30 minutes
• HARD DRY	: 2-3 hours.
• SANDING TIME	: After 2 hrs.
• OVERCOATABILITY	: After 2 hrs.
• FLEXIBILITY	: Passes bending mandrel of 1/4"
• CROSS HATCH TEST	: Passes
• OIL & PETROL RESISTANCE	: Good

Directions for Use

Thin down to spraying viscosity using thinner N.C.033 (it cannot be brushed) and start applying by cross-lap method. Allow drying for 2 hrs. And start wet sanding using the finest grain paper till a silky smooth surface is obtained. The surface is ready to accept synthetic or N.C.top coats.

Notes

N.C.P.S., can be supplied in white shade, provided the minimum quantity is 150 litres.

Disclaimer

PRODUCT CODE 2256
ROSALEE N.C.PRIMER SURFACER WHITE

—

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020