

PRODUCT CODE : 3000

RICHWOOD ONE PACK TABLE TOP CLEAR GLOSSY

Scope

The internationally accepted method of producing N.C. Clear lacquers is to mix nitrocellulose with non-drying short oil alkyd, a plasticizer and solvents in appropriate proportion. To reduce cost for unhealthy competition, a large number of manufacturers use less of nitrocellulose and more of an alkyd. Even solvent blend (used for making clear) must be well balanced consisting of low/medium/high boiling solvents along with latent solvents and diluents. The general practice is to use maximum quantity of cheaper solvents. Such formulations, though work, yield inferior results.

Richwood N.C. Clear Glossy is a very well balanced product.

Areas of Application

All metals and also wood.

Surface Preparation

See the pamphlets on surface preparation of metals and surface preparation of wood.

Technical Data

- APPEARANCE : Free flowing, light pale yellow liquid.
- REDUCED VISCOSITY OF N.C. 033 THINNER (1:1) : 25 to 30 seconds
- SPRAYING VISCOSITY : 22 to 25 seconds
- THINNER TO BE USED : N.C. 033 thinner
- DUST FREE TIME : 5 to 10 minutes
- THUMB IMPRESSION FREE : 40 to 50 minutes
- HARD DRY : 24 hrs.

Directions for Use

Prepare the surface as recommended above. Thin down the clear to spraying viscosity. Apply three coats, each at an interval of twenty or thirty minutes. Allow to dry when after rubbing compound be used for eliminating all blemishes. Finally polish, using wax polish but preferably silicones polish.

Notes

Also available as matt lacquer. Ensure, the compressed air used is totally free from moisture.

PRODUCT CODE - 3000
RICHWOOD ONE PACK TABLE TOP CLEAR GLOSSY

1

Disclaimer

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020