

**PRODUCT CODE-4050**  
**ROSALEE METAL PRIMER REDOXIDE**

● **Description**

All ferrous surfaces tend to catch rust even if the humidity is low. Rust destroys iron. Therefore, some of protection has to be provided. The most economic method is to apply a coat of red oxide primer. Red oxide is the cheapest anti corrosive pigment.

ROSALEE METAL PRIMER REDOXIDE is made with an alkyd medium, which has its own strength to fight corrosion.

● **Areas of Application**

All types of iron surface. It can be brushed as well as sprayed.

● **Surface Preparation**

The surface to be painted has to be free from oil, grease and rust. The best way to achieve the objective, sand blasting is the best. Alternatively, RUSTOSAN P-017 should be used. It is a 3-in-1 compound. It helps in removing oil, grease and rust in single operation. Then after, the surface must be made dry, using sunlight or by blowing hot air.

● **Technical Data**

Appearance	:	Free flowing liquid with the shade of red oxide.
Viscosity on FC4	:	160 ± 10 sec. at 30°C.
Weight per litre at 30°C.	:	1.30 ± 0.02 kg./ltr.
Brushing viscosity	:	70-80 sec.
Spraying viscosity	:	25-30 sec.
Thinner to be used	:	Syn. Thinner 011
Drying time	:	Touch dry : 15 to 20 min. Surface dry : 40 to 50 min. Hard dry : 24 hrs.
Sanding time	:	Over night.
Flexibility after 24 hrs. drying	:	Passes the bending mandrel of 1/4"
Covering capacity	:	10-12 sq. mtr. per coat

● **Directions for Use**

Prepare the surface as directed above. Thin the primer to appropriate viscosity for brush or for spraying. Go ahead with the job.

**PRODUCT CODE-4050**  
**ROSALEE METAL PRIMER REDOXIDE**

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

**By Mrigold Paints Pvt Ltd**

C-1/10 GIDC Estate,  
Vallabh Udyog Nagar 388120  
Anand, Gujarat  
INDIA

**PRODUCT DATA SHEET**

ISSUED: JUNE 2020