

ROSALEE PRIMER REDOXIDE ZINC CHROME PRIMER TO IS-2074

Scope

Iron oxide (red oxide) by itself has good corrosion resistance. But, where better resistance is needed, a combination of iron oxide and zinc chrome is used while preparing the primer. The minimum quantity of zinc chrome needed is 20% of the total pigment. Every film of primer accepts moisture from the air, which in turn is the main cause of rusting. Zinc chrome pigment (under moist conditions) dissociates itself into zinc and chromic acid. The latter offers what is called passivation thereby taking much longer time to start rust.

Areas of Application

Any type of steel structure that needs better protection from corrosion (created by humidity) needs zinc-zinc chrome primer. It is massively used to protect large steel structures like bridges and towers and also be used on smaller articles fabricated or casted.

Surface Preparation

The surface must be free from oil, grease and rust. The best way to achieve this is to use sand blasting or 7-tank phosphate system. However, if for any reason, it is not possible, use can be made of rustosan, which removes oil, grease and rust in single operation.

Technical Data

- APPEARANCE : Free flowing liquid showing red oxide colour.
- VISCOSITY : 120 ± 10
- THINNER TO BE USED : Syn. Thinner 011
- WEIGHT PER LITRE : 1.37 ± 0.02 kg/ltr.
- DRYING TIME : Surface dry : 15-20 min.
- THUMB IMPRESSION FREE : 40-50 MIN.
- HARD DRY : 24 hrs.
- SCRATCH HARDNESS : Passes the load of 1000 gms.
- CROSS HATCH TEST : Passes the test.
- FLEXIBILITY : Passes the bending mandrel of 1/4"
- SALT SPRAY RESISTANCE : Minimum 96 hours.
- HUMIDITY RESISTANCE:

Direction for Use

Prepare the surface as directed above and start brushing or spraying with adequate quantity of thinner 011 preferably wet sand after 2-3 hours, to get a very smooth surface.

PRODUCT CODE - 4054
ROSALEE RED OXIDE ZINC CHROMATE PRIMER IS 2074

Notes

As stated earlier (under introduction) minimum 14% on total pigmentation should be zinc chromate, to fulfill the conditions of is-2074.

Now, zinc chromate pigment is very expensive and so, many unscrupulous manufacturers use less than 14% of total pigments and fool the customers. Therefore, we recommend, the consumer should get the product analysed in any good laboratory before buying the product or ask the manufacturer to submit analytical report along with the supply.

Besides, in the market, is also available redoxide-zinc chrome primer to is 2074-p. The affix “p” stands for performance and is much cheaper because it contains either very little of zinc chrome. Here the results are achieved by using a special anti corrosive additive. Thus, where there is no statutory requirement to use the genuine primer, the one, 2074-p can be used.

Disclaimer

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users’ responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020