



PRODUCT CODE - 4111
KARATE 2K ALUMINIUM

Scope

Aluminium paint is the most cost-effective coating to withstand corrosion of mild steel. Besides, it is heat and light reflective whereby, the ambient temperature under a roof coated therewith, is lower by 5-7°C. To get the best effect of shiny aluminium, use must be made of fine leafing aluminium paste. Also, the medium used must have the lowest viscosity with highest possible solids and lowest acid value. This is necessary for getting the best leafing value, which provides long lasting brightness. Karate aluminium paint is made with all the above said characteristics. It is dual pack : medium in a bigger tin and paste into a smaller container. For the sake of convenience, the smaller pack is soldered to the lid of the larger can and the paste can be easily mixed into the medium can. It is necessary to have dual package because the leafing value of aluminium gets lowered if the medium and paste (aluminium) are combined into one pack.

Areas of Application

All mild steel articles, which need water resistance, can be coated with karate aluminium paint. It can be brushed as well as sprayed. It can safely be used for inside/outside coating of potable water tanks. It is also excellent for coating mild steel roofing sheets, under which the temperature will be lower by 5-7°C against outer temperature.

Surface Preparation

See the pamphlet on surface preparation of metals.

Technical Data

- APPEARANCE : Medium - Yellowish brown. Paste - Sparkling aluminium.
- VISCOSITY OF MEDIUM : 14 sec. At 30o c.
- VISCOSITY OF MIXED PAINT : 15sec. At 30o c.
- WEIGHT PER LITRE OF MEDIUM : 0.84 kg/ltr.
- WEIGHT PER LITRE OF THE MIXED PAINT : 0.88 kg/ltr.
- SPRAYING VISCOSITY. : 15 sec.
- BRUSHING VISCOSITY : 15 sec.
- THINNER TO BE USED : NONE
- DRYING TIME : Touch dry : 45 to 60 min.
Dust free : 3 to 3½ hrs.
Thumb impression free : 4 to 4½ hrs.
Hard dry : 24 hrs.
- RECOATABILITY : 2 – 2½ hrs.

PRODUCT CODE - 4111 KARATE 2K ALUMINIUM

Directions for Use

Prepare the surface as directed earlier. Mix medium and paste thoroughly. Do not use high-speed mixer because under shear, aluminium flakes lose their leafing capacity. Do not use any thinner because the medium is pretty thin and does not need any further thinning when mixed with paste. Start brushing or spraying

Notes

If possible, use the mixed paint within 48 hours. Storage for a longer time reduces leafing value and the full brightness gets reduced to some extent.

Disclaimer

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020