

PRODUCT CODE - 7102
ROSALEE HR 400 - UP TO 400 °C – SILICON PAINT

Composition

This is silicon polymer based product which combines heat resistance up to 400° c.

Recommended Applications

This coating can be applied where dry heat resistance up to 400° c is required. Areas like chimneys, ovens, stack, exteriors of boilers etc. Can be coated with this paint.

Technical Data

COLOUR	:	Aluminium
FINISH	:	Smooth and shiny
VISCOSITY	:	25 to 35 sec by fc no.4@ 30° c.
WEIGHT/LITRE	:	0.93 ± 0.05 kg/ltr
VOLUME SOLIDS	:	30 ± 2%
THEORETICAL SPREADING RATE	:	12 to 14 sq. Mtr/ ltr@ dft of 25 microns
DRYING TIME	:	Surface dry : 1 to 2 hrs @ 30° c Hard dry : 30 min @ 180°c
DRY FILM THICKNESS	:	20 to 25 microns
HEAT STABILITY	:	Up To 400° C. In Dry Heat

Typical Application Systems And Equipments

It is recommended to apply heat resisting aluminium paint on a surface blasted up to sa 2½. If blasting is not possible clean the surface with wire brush and sand papers to remove old paint and loosely adherent rust. The surface must be clean and dry, free from oils, dirt and moisture before application.

This product is generally applied by brush and conventional spray application

Brush application:

Thinner	:	synthetic thinner 011
Addition	:	5 %, if required

Conventional spray application setting:

Thinner	:	synthetic thinner 011
Addition	:	5 %, if
required Nozzle orifice	:	1.2 -1.4 mm
nozzle pressure	:	40-50 psi

PRODUCT CODE - 7102
ROSALEE HR 400 - UP TO 400 °C – SILICON PAINT

2

Surface Preparation

This paint can be directly applied over surface, which must be blasted up to sa 2½. If blasting is not possible clean the surface with wire brush and sand papers to remove old paint and loosely adherent rust. The surface must be clean and dry, free from oils, dirt and moisture before application.

Health And Safety

Heat resisting aluminium paints contain organic solvents and aluminium pigments. Mixing and handling of this product this paints must be carried out with taking proper safety measures to avoid skin contacts, eye contacts, and inhalation of solvent vapours and mist of the paint spray. The painting must be carried out in a well ventilated spray booths fitted with proper exhaust systems. If painting is to be done on site, care must be taken that along with the spray painter; other people in the nearby area are also protected in the same manner as the painter. Polyurethane paints if swallowed immediately contact a doctor.

Disclaimer

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for any loss or damage whatsoever occurred including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

By Mrigold Paints Pvt Ltd
C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET
ISSUED: JUNE 2020