

PRODUCT DATA SHEET

Product Code 7553

MARIPOXY 800

HIGH SOLID HIGH BUILD EPOXY MASTIC COATING

Description	Maripoxy HS Epoxy Mastic is a low VOC, two component high build, high solids epoxy coating. It is cured with Polyamide and on curing it forms a hard and tough coating. A fast drying version also available suitable for application at low temperatures in winters.
Uses	It can be used as- <u>Primer, Intermediate Coat or finishing coat where low VOC and high film build is required.</u> It is suitable for use at both new construction and in maintenance offering good corrosion resistance. It can be over coated with Polyurethane coatings to get excellent outdoor durability.

PHYSICAL PROPERTIES

Colour	Grey, MIO and other selected range of colors
Finish	Eggshell to Semi glossy, Smooth and Free from any surface defects
Density	1.7 Kg/Liter
Volume Solid %	80±2
Theoretical Coverage	About 8 Sq. Meter / Liter at 100 Micron DFT(without loss factor)
Flash Point	25 °C
Touch Dry	2.5 Hours at 30 Degree C
Hard Dry	Overnight
Full Cure	7 days
VOC	205 ± 3 Grams /Liter
Shelf Life	2 Years when stored in shade below 35 Degree Centigrade.
Service Temperature	115° C.

APPLICATION DETAILS

Mixing Ratio - Base: Hardener	4:1 by Volume
Application Method	Airless Spray, Brush, Roller and by Flow.
Pot Life	2.0 Hours at 30°C (Pot Life decreases with increase in room temperature)
Nozzle Size	0.018"-0.025"
Pressure by Airless Spray	240-250 Bar
Dry Film Thickness (DFT)	100- 120 Microns (viscosity can be adjusted to achieve required DFT but thinning not to exceed more than 10% of thinner no 055)
Wet Film Thickness (WFT)	130- 160 Microns
Over coating Interval	Minimum – 6 Hours and Maximum 4 Weeks

MARIPOXY HIGH SOLID HIGH BUILD EPOXY MASTIC COATINGS

SURFACE PREPARATION	<p>New steel: Surface should be free from all dust, dirt, oil and grease etc. Salts and other contaminants can be removed by high pressure fresh water wash. Substrate to be blasted to Sa 2 ½ or ST 2-3. A surface profile of 50-75 microns (2-3 mils) is recommended.</p> <p>Maintenance of old painted structure: Clean already painted surface with detergent to remove dust, dirt, oil and grease etc. Salts and other contaminants can be removed by high pressure fresh water wash. Remove all rust and loose material preferably by dry abrasive blasting. Minor areas may be power tool cleaned.</p>
APPLICATION CONDITIONS	Avoid use of paint when atmospheric temperature is below 10 Deg. C. Temperature of Paint to be sprayed need to be maintained above 15 degree centigrade.
PREVIOUS COAT	Can be used Direct on Metal or on Maripoxy HB ZP Primer
SUBSEQUENT COAT	Marithane PU Topcoat
CAUTION	Epoxy Paints are prone to Chalking and Fading on direct exposure to Sunlight. It is recommended to overcoat Epoxy primer/Mid Coat with PU Paint to get good outdoor durability and maintain aesthetics.
SAFETY	Maripoxy Epoxy Paints are solvent based products, user need to take safety precaution which are applicable to all the petroleum based inflammable products. Painting should be done in open and ventilated place. Use Foam based fire extinguishers in case of fire. Keep it away from direct fire/ flame and store the product under the shade below 35 degree Centigrade.

Issued By Marigold Paints Private Limited,

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions.*

Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.