

PRODUCT CODE 4056
ROSALEE UNIVERSAL PRIMER WHITE

● **Areas of Application**

All types of wood, particle board, plywood, nu-wood or Any iron surface, Any cement concrete surface or asbestos cement sheets, which may have hair cracks or which is micro porous. The primer is required to fill up such surface defects.

● **Surface Preparation**

All loose grains on the surface must be eliminated with the help of dry fine sand paper no. 400. The sanding has to be horizontal to the grains. Wipe out all loose particles, dust etc. Using dry rag pad. The surface must feel smooth under fingers.

● **Technical Data**

- | | |
|----------------------|-----------------------------------|
| ● APPEARANCE | : Free flowing, white |
| ● VISCOSITY | : 150 ± 10 second in FC 4 @ 30°C. |
| ● BRUSHING VISCOSITY | : 60 to 70 seconds. |
| ● THINNER TO BE USED | : Syn. Thinner 011 |
| ● TOUCH DRY | : 40 to 50 minutes |
| ● HARD DRY | : 24 hrs. |
| ● RECOATABILITY | : After 3-4 hours. |

● **Directions for Use**

After preparing the surface as stated above apply two to three coats either by brushing or by spraying. While brushing cross-lap method should be used. Each coat must be allowed to dry for at least three hours and each coat must be dry-cut using no. 400 sand paper. Preferably, dust free atmosphere must be created. Cutting must be done horizontally to the wood grains, till a very smooth – silk smooth surface is obtained with sheen. The surface will be ready to accept topcoats.

● **Notes**

The wood must be free from moisture. In case of high porosity as in particle board, apply one thin coat of synthetic putty, using a spatula. This will cover all surface defects. Remember to dry cut synthetic putty film, using very fine sand paper.

ROSALEE WOOD PRIMER WHITE / PINK

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations*, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020