

PRODUCT CODE 5001
ROSALEE STIPPLE FINISH PAINT

● **Scope**

There are a large number of engineering articles, made of cast iron or of mild sheet, where it is difficult to make the surface, very smooth, even after application of primer and putty, such items, when coated with any finishing paint, have a tendency to highlight all surface defects, unless the finishing paint is dead matt. To overcome this problem, the best solution is to apply a coat or two Stipple finish. It covers all surface defects offers an aesthetic appeal.

● **Areas of Application**

Any Stipple surface having pores or uneven surface where hiding of surface defects is important.

● **Surface Preparation**

The surface should be free from rust, oil or grease. The best way to achieve the objective is, sand blasting or 7 tank phosphating system. If for some reason, it is not possible, rustosan should be used. It is a 3-in-1 compound, which removes oil, grease and rust in single operation. Besides, a light coat of zinc-iron phosphate is formed which gives better adhesion to paint and also offers corrosion resistance.

● **Technical Data**

- | | |
|------------------------|--|
| • APPEARANCE | : Free flowing liquid, free from lumps and showing an
Appropriate shade |
| • VISCOSITY BY FC4 CUP | : 170 ± 10 sec. At 30° c. |
| • THINNER TO BE USED | : Thinner 077 or Thinner 011 |
| • DRYING TIME | : Touch dry : 5 to 10 min.
Dust free : 10 to 15 min.
Surface dry : 20 to 25 min.
Hard dry : 24 hrs. |
| • FLEXIBILITY | : Passes 1/4 inch bending mandrel. |

● **Directions for Use**

Prepare the surface as directed above. Thin the paint for spraying consistency and first, apply a mist coat (very thin coat). Apply second coat with medium pressure and you will see a built up of uniform Stipple finish.

● **Notes**

Use of a correct thinner is very essential for getting uniform patterns of Stipple.

PRODUCT CODE 5001

ROSALEE STIPPLE FINISH PAINT

The Product is for Industrial use only. Product data given here *is correct to the best of our knowledge but their accuracy may vary depending upon the quality of the substrate, application parameters and atmospheric conditions affecting the performance of the product. Therefore the users are advised to make their own tests to determine the suitability of products for their own purposes under present conditions. Unless agreed upon in writing, we do not accept any liability for the performance of the product. We hereby disclaim any warranties or representations, liability, including but not limited to negligence, injury, consequential losses or damages arising from the use of the Products as recommended above. Product data are subject to change without notice.*

By Mrigold Paints Pvt Ltd

C-1/10 GIDC Estate,
Vallabh Udyog Nagar 388120
Anand, Gujarat
INDIA

PRODUCT DATA SHEET

ISSUED: JUNE 2020